



Manufacturers of BIO-SAFE Technology

## Application Data Sheet:

# HI-LACRYL

## COLOUR HI-LIGHTER

---



### APPLICATION:

- **ALWAYS TEST PRODUCT ON A SMALL AREA FIRST** and allow a 24 hour cure time to determine the ease of application and desired results for both stain resistance and appearance that will meet YOUR requirements.
- Allow new concrete to cure for at least 14 days prior to application.
- Remove all dirt, stains, dust, grout haze and foreign material.
- Colored concrete should be wet down, then a 30 part water to 2 part hydrochloric acid mixture applied, scrubbed lightly and thoroughly rinsed off.
- For non colored concrete, the same should be done with 20 parts water to 1 part hydrochloric acid solution. **DO NOT USE HYDROCHLORIC ACID ON SANDSTONE.** (For this we suggest **D-SCALE**).
- If an unsealed surface gets wet, allow 24 hours for drying.
- Initial coats 4 - 8 square meters and second coats 7 - 10 square meters per litre, depending on the porosity of the substrate.
- Use a brush, broom or roller.
- 1 or 2 coats should be applied depending on the finish required and the porosity of the substrate.
- Application should not be made when temperature is over 30°C or below 5°C.
- If using as a COLOR ENHANCER for SANDSTONE it is best to pre-seal area with **SILCOPEL** or **CONSOLIDATE** for best results. Allow pre-sealer 24 - 48 hours to cure before applying **HI-LACRYL**.

---

#### Disclaimer – User Guide

*Solutions - Sealers for Stone & Tile believes the information contained in this document is accurate as **general advice only**. As general advice only it has been prepared without taking into account the objectives, problems or needs of the reader. Solutions – Sealers for Stone & Tile has presented this information as a guide only and accepts no liability for any loss or damage caused by any error in, or omission from, this document. Solutions – Sealers for Stone & Tile has no control over the use or misuse of this product, therefore no warranty expressed or implied shall be given. Solutions – Sealers obligations shall be limited to only replacing product PROVEN defective. The user MUST educate themselves on the performance value, application rates, substrate type and environment before product is applied, a TEST area is always highly recommended.*